

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 631 999 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
03.09.1997 Bulletin 1997/36

(51) Int. Cl.⁶: **C04B 41/49**

(21) Application number: **94109082.1**

(22) Date of filing: **14.06.1994**

(54) Cationic emulsions of alkylalkoxysilanes

Kationische Emulsion von Alkylalkoxysilanen

Emulsion cationique des alkylalkoxysilanes

(84) Designated Contracting States:
BE DE FR GB IT NL

(30) Priority: **30.06.1993 US 84867**

(43) Date of publication of application:
04.01.1995 Bulletin 1995/01

(60) Divisional application: **96107699.9**

(73) Proprietor: **OSI SPECIALTIES, INC.**
Danbury, Connecticut 06817-0001 (US)

(72) Inventors:
• **Chen, Ming J.**
Garnerville, N.Y. 10923 (US)
• **Chaves, Antonio**
White Plains, N.Y. 10605 (US)

(74) Representative: **Wibbelmann, Jobst, Dr., Dipl.-**
Chem.
Wuesthoff & Wuesthoff,
Patent- und Rechtsanwälte,
Schweigerstrasse 2
81541 München (DE)

(56) References cited:
US-A- 4 648 904 **US-A- 5 209 775**
• **DATABASE WPI Derwent Publications Ltd.,**
London, GB; AN 94-148131 & JP-A-6 093 254
(TOYO INK) 5 April 1994
• **DATABASE WPI Derwent Publications Ltd.,**
London, GB; AN 82-60673E & JP-A-57 095 882
(TORAY SILICONE) 14 June 1982

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**Background**

Concrete structures can undergo accelerated deterioration due to corrosion of the reinforcing steel rods. The corrosion is caused by the gradual introduction of chloride into the concrete from deicing salts. Applying penetrating sealers can greatly diminish the intrusion of chloride into the concrete.

Solutions of alkyltrialkoxysilanes in organic solvents have been used very effectively to impart water repellent properties to porous masonry substrates such as mortar and concrete. These formulations penetrate the masonry substrate and provide a significant hydrophobic layer. However, solvent base formulations are undesirable due to the large amount of volatile organic components that are released into the air during their use. Various state regulations prohibit the volatile organic content (VOC) of an architectural coating from exceeding four hundred grams per liter.

The prior art solvent base coatings have not met these regulations. To reduce the amount of organic compounds released into the air, preparations of aqueous emulsions of alkyltrialkoxysilanes have been reported.

The utility of silanes in such aqueous emulsions, especially alkoxysilanes, as masonry water repellents is a widely known use because of their hydrophobic nature. For example, U.S. Patent No. 4,648,904 issued to DePasquale and Wilson teaches a porous masonry water repellent composition comprising: a hydrolyzable silane, an emulsifying agent and water. U.S. Patent No. 4,877,654 issued to Wilson teaches a similar composition but also contains a buffering compound to maintain the composition within the pH stable range. U.S. Patent No. 5,074,912, issued to Liles and Klein also teaches a water repellent composition for treating porous substrates consisting of an emulsion containing water, at least one surfactant, and a siloxane. However, the emulsifiers taught therein are generally nonionic surfactants and only one type of silane (the active ingredient) may be used at a time in each emulsion. It has been found that nonionic emulsifiers, in particular highly ethoxylated surfactants, reduce the hydrophobic effect of these compositions. This leads to an increase in water absorption of the masonry material and in most cases a reduction in penetration depth of the silane.

Another example of prior art aqueous emulsions is taught in U.S. Patent No. 4,433,013 issued to Puhlinger, which discloses a water-sealant for inorganic porous mineral substrates which comprise an emulsion of at least one silane, one deactivatable surfactant, an organic alcohol, and water. The surfactants taught as useful therein include fatty acid esters, and particularly alcohol/alkylene oxide adducts.

Moreover, in unrelated fields, the manufacture and use of quaternary ammonium pendant siloxane copolymers have been known. See U.S. Patent No. 4,895,964, issued to Margida. The uses in the prior art of such quaternary polysiloxanes have been in cosmetic preparations, as disclosed in the U.S. Patent No. 4,891,166, issued to Shaefer and Krakenberg and in waterproofing compositions with good fungicidal and mildewcidal properties, as disclosed in European Patent Application, Publication No. 0,469,624, to Yoshioka.

Summary of Invention

The present invention teaches masonry water repellents comprising aqueous emulsions of alkylalkoxysilanes with either a quaternary ammonium surfactant or a mixture of a quaternary ammonium surfactant with an amino and/or a nonionic surfactant. The alkylalkoxysilane is present at a level of about one to sixty weight percent of the final solution weight. The surfactants are present at levels of about 0.05 to 25 weight percent of the final solution weight. The useful quaternary ammonium surfactants are alkyltrimethyl or dialkyldimethyl ammonium compounds. Amino and nonionic surfactants are used as additives to the quaternary surfactants. The types of nonionic surfactants contemplated herein are alkylamines and alkyl acetylenic alcohols. Thus the invention relates to an aqueous emulsion consisting essentially of (a) 1.0 to 60 weight % of a silane; (b) 0.05 to 25 weight % of a quaternary ammonium compound of the general formula $R^1_a(R^2)_{4-a}N^+X^-$, where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length, and X^- is an inorganic or organic anion.

Further embodiments of the invention are set forth in claims 2 to 12.

Description of Invention

The present invention relates to the preparation of stable aqueous emulsions which impart hydrophobic properties to masonry materials and which penetrate into the masonry material to provide a significant hydrophobic layer. The term "masonry" is intended to include any porous inorganic substrate, particularly building compositions and including, but not limited to, structural ceramics such as common brick, paving brick, face conduits, roofing tile, flue lining, cements such as Portland cement, calcined gypsum products, molding and building plaster and stucco, magnesia cement, insulation products such as electrical and thermal insulators (diatomaceous earth brick) and porcelain spark plugs. The term also includes stone, tile, artificial stone, adobe, concrete and reinforced concrete such as found in roadways, bridge decks, airport runways, parking garage decks, and other concrete building structures. The hydrophobic properties imparted by the emulsion of the present invention applied over masonry surfaces protect the surfaces from

corrosion, acidic rain, salt water and other degradents which water could otherwise deliver into the masonry.

An aqueous emulsion of the present invention consists of an alkylalkoxysilane or mixtures of alkylalkoxysilanes, emulsifiers and water. Optionally, a buffer may be added to maintain the pH of the emulsion in the preferred range of between 6 and 8. The alkylalkoxysilanes are the hydrophobic active ingredients in the emulsion that block the penetration of water into the masonry. The water is the solvent that carries the active ingredient into the masonry. The emulsifier is necessary to solubilize the silane in water. The buffer controls the pH of the solution.

The alkylalkoxysilanes for use herein are of the general structure $R^1_a Si(OR^2)_{4-a}$ where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain configuration or aryl or aralkyl groups, R^2 may be C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3). The preferred R^1 is C_5 to C_{12} alkyl groups and R^2 is C_2 to C_4 alkyl groups. The most preferred silane for use herein is octyltriethoxysilane and octyltriisopropoxysilane. Alkyltrimethoxysilanes tend to hydrolyze more readily and decrease the shelf life of the emulsion and so are not preferred.

Moreover, mixtures of silanes may be used in emulsions of the present invention. By using a mixture of silanes in the emulsion one can choose one silane for its hydrophobic properties and another for its ability to penetrate masonry. Previously, mixtures of silanes could not be used because it was difficult to match two different silanes to a single emulsifier. Specific examples of silanes used in accordance with the present invention include, but are not limited to, methyltriethoxysilane, methyltri-n-propoxysilane, ethyltriethoxysilane, dimethyldimethoxysilane, dimethyldiethoxysilane, ethyltri-n-propoxysilane, propyltriethoxysilane, propyltri-n-propoxysilane, butyltriethoxysilane, dibutyldimethoxysilane, isobutyltrimethoxysilane, di-isobutyldimethoxysilane, isobutyltriethoxysilane, 4-chlorobenzyl triethoxysilane, 4-bromobenzyl tri-n-propoxysilane, phenyltriethoxysilane, octyltriethoxysilane, octyltriisopropoxysilane, dodecyltribromosilane, tetradecyltriethoxysilane, hexadecyltriethoxysilane, octadecyltriethoxysilane, mixtures thereof, and admixtures thereof with dimers, trimers and other oligomers thereof.

The emulsifiers for use herein include a quaternary ammonium surfactant or a mixture of quaternary ammonium surfactants with amino or specific nonionic surfactants. The quaternary ammonium surfactants are alkyl quaternary ammonium compounds. The quaternary ammonium compounds of the present invention are of the formula $R^1_a R^2_{4-a} N^+ X^-$ where R^1 is C_8 to C_{22} alkyl group, R^2 are relatively short alkyl groups of 1-3 carbons in length and a is 1 or 2. Specific examples of quaternary ammonium surfactants useful in accordance with the present invention include, but are not limited to the following examples (tradenames and trademarks): ARQUAD 2C-75, C-33W, C-50, 2HT-75, S-50, T-50, 12-37W, 12-50, 16-29W, 16-50 and 18-50 (commercially available from AKZO Chemicals, Inc. of Chicago, Illinois), JET QUAT C-50, S-2C-50, S-50, T-2C-50, T-50 and 2C-75 (commercially available from Jetco Chemicals, Inc. of Corsicana, Texas), M-QUAT 32-2475 (commercially available from Mazer Chemicals, Inc. of Mission Viejo, CA), TINEGAL MR-50 (commercially available from Ciba-Geigy Corp. of Basel, Switzerland), TOMAH Q-17-2, Q-18-15, Q-311, Q-511 and Q-D-T (commercially available from Tomah Products, Inc., a division of Exxon Chemical Co. of Milton, WI), and VARIQUAT A-200, B-200 and K-300 (commercially available from Sherex Chemical Co., Inc. of Dublin, Ohio).

Co-surfactants may be used as additives with the quaternary ammonium surfactants. The types of surfactants useful for such a purpose are alkyl amines, which become protonated in the aqueous solution, and nonionics which are hydroxylated ethoxylated acetylenic hydrocarbons, such as ethoxylated tetramethyl decynediol (SURFYNOL 420®), available from Air Products of Allentown, Pennsylvania). In distinction, ethoxylated amines (e.g., bis(2-hydroxyethyl) cocoamine (ETHOMEEN® C/12 available from Akzo Chemicals Inc. of Chicago, Illinois)) have been found not to be effective for this purpose. The ethoxylated acetylenic hydrocarbon nonionics, for this purpose, should only be present at about 0.1 to 1.0 weight percent of the total emulsion and preferably about 0.3 weight percent. The alkyl amines have been found effective at weight percentages about equal to those of the quaternary ammonium surfactant present.

Specific examples alkyl amines useful as co-surfactants in accordance with the present invention include, but are not limited to, dodecylamine, hexadecylamine, octadecylamine, amines derived from coconut oil, hardened tallow, tallow, soya, methyl dicoco amine, methyl dihydrogenated tallow amine, dimethyl cocoamine, dimethyl dodecyl amine, and dimethyl hexadecyl amine. Specific examples of nonionic surfactants useful as co-surfactants in accordance with the present invention include, but are not limited to, SURFYNOL® 61, 82, 104, 420, 440 and 465 (available from Air Products).

Optionally, a small amount of organic solvent can be used as an additional stabilizer. These organic solvents have a synergistic effect on the emulsion and are not intended to be added at the level of a solvent, but act rather as a stabilizer of the emulsion. Said solvents should be added at less than 10.0 weight percent of the emulsion, and preferably at about 1-2 weight percent. Specific examples of solvents useful in accordance with the present invention include, but are not limited to, alcohols such as methanol, ethanol, propanol, 2-propanol, butanol, 2-methyl-2-propanol, 2-butanol and pentanol.

The silane may be present in an amount ranging from 1.0 to 60 weight percent of the emulsion. Varying the amount of silane in the emulsion changes the performance of the emulsion since the silane is the active ingredient. The emulsifier is present in an amount ranging from 0.05 to 25 weight percent of the emulsion. The greater the amount of silane, the greater the amount of emulsifier required to solubilize the silane in water. The weight ratio of silane to emulsifier should be about 1:1 to 120:1, preferably from 4:1 to 20:1 and in particular about 10:1. Water is present in an amount ranging from 15 to 98.95 weight percent of the emulsion.

The aqueous emulsions are typically prepared by mixing the surfactant or mixture of surfactants with an alkyltri-alkoxysilane or a mixture of alkylalkoxysilanes. Water is then added and the mixture is blended to provide a white, milky emulsion. The pH of the resulting emulsion may be adjusted to provide a final emulsion with a pH of 7.0 ± 1.0 . A pH outside of this range is possible, but it shortens the shelf life of the emulsion. Substances which can be used to adjust the pH are organic or inorganic buffers including sodium acetate, sodium citrate, sodium carbonate, sodium bicarbonate, sodium hydrogen phosphate, sodium dihydrogen phosphate, the corresponding potassium salts, and organic amines and their salts. When organic amine surfactants are used as co-emulsifiers, the addition of buffer usually is not required because the pH is normally in the desired range of 6 to 8.

The emulsions of the present invention may be applied onto the surface to be protected in a variety of ways that are well known in the art, including, but not limited to, brushing, spraying and rolling the emulsion on the surface.

When an emulsion of the present invention was applied at the rate of $3.07 \text{ m}^2/\text{l}$ (125 square feet per gallon) as a single coat, the industry standard for testing, it reduced the water gain of a two-inch concrete tube by approximately 70 percent and the silane had a penetration depth of at least 0.51 cm (0.2 inches). A typical emulsion prepared with surfactants has a penetration depth of only 0.254 cm (0.1 inches).

Examples

Coating and Testing Procedure

The penetrating sealers described below were applied to 5.08 cm (two-inch) concrete tubes at a rate of $3.07 \text{ m}^2/\text{l}$ (125 square feet per gallon) with a small, bristle brush and allowed to cure on a wire rack for two days at ambient conditions. The coated tubes were weighed and then completely immersed in a water bath so that the concrete was more than one inch below the water surface. The cubes were weighed daily and the percentage weight increase was determined. When the soaking test was completed, the cubes were allowed to dry at ambient conditions in a laboratory hood. After the cubes were allowed to dry, they were broken in half. The inner surface of each cube was sprayed with water and the depth of penetration of the sealer was determined as a visible dry area of the concrete below the coated surface. This was easily measured with a ruler or caliper. The results of the sealers described below are set forth in Table I.

Example I

To 13.4 grams of octyltriethoxysilane was added 3.0 grams of dimethyldicocoammonium chloride (ARQUAD® 2C-75 available from Akzo Chemicals Inc. of Chicago, Illinois). The mixture was stirred with a stirring bar for 30 minutes. To this mixture was then added 33.6 grams of deionized water and the mixture was stirred vigorously. A milky white emulsion resulted. The pH of the emulsion was adjusted with sodium phosphate dibasic to give a final pH of 7.4.

Example II

To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD® 2C-75 in an Oster blender and mixed at low speed for one minute. 58.0 grams of water buffered to a pH of 7.0 with a phosphate buffer was added to the mixture and the mixture was stirred at a high speed for five minutes resulting in a white, milky emulsion. The pH of the resulting emulsion was found to be 6.8.

Example III

To 3.5 grams of octyltriethoxysilane and 0.5 grams of 1,10-bis(trimethoxysilyl)decane was added 0.4 grams of ARQUAD® 2C-75. The mixture was stirred with a magnetic stirring bar. To this mixture was then added 5.6 grams of deionized water and the mixture was stirred vigorously. A white milky emulsion resulted. To the emulsion was added 0.02 grams of SURFYNOL® 420. The emulsion was stirred for an additional thirty minutes.

Example IV

To 3.5 grams of octyltriethoxysilane and 0.5 grams of 1,10-bis(trimethoxysilyl)decane was added 0.3 grams of ARQUAD® 2C-75 and 0.05 grams of dimethyl di(hydrogenated-tallow)ammonium chloride (ARQUAD® 2HT75 available from Akzo Chemicals Inc. of Chicago, Illinois). The mixture was stirred with a magnetic stirring bar. To this mixture was added 5.65 grams of deionized water and the mixture was stirred vigorously for four hours. A white milky emulsion resulted.

Example V

To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD® 2C-75, and 2.0 grams of cocodimethyl amine (ARMEEN® DMCD available from Akzo Chemie America). The mixture was blended at low speed. To this mixture was added and blended at high speed 56.0 grams of water. A white emulsion resulted.

Example VI

To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD® 2C-75 and 2.0 grams of ARMEEN® DMCD. The mixture was stirred. To this mixture was added and mixed at high speed 55.7 grams of water. Finally, 0.3 grams of SURFONYL 420 was added and the mixture was stirred for thirty minutes.

Comparative Example I

To 30 grams of absolute ethyl alcohol was added 20 grams of octylmethoxysilane to make a 40% by weight silane solution.

Comparative Example II

To 20.0 grams of octyltriethoxysilane was added 0.56 grams of octylphenoxypolyethoxy ethanol and 0.24 grams of octylphenoxypolyethoxy ethanol [differentiate] in an Oster blender. The mixture was stirred at a low speed for one minute. Deionized water, 29.2 grams, was added quickly and the mixture was blended at a high speed for five minutes. A white, milky emulsion resulted.

Comparative Example III

To 30.0 grams of octyltriethoxysilane was added 0.42 grams of alkyloxypolyethyleneoxy ethanol (primary alcohol) and 0.78 grams of alkyloxypolyethyleneoxy ethanol (secondary alcohol) in an Oster blender at a low speed for one minute. 43.8 grams of deionized water was added and the mixture was blended for five minutes at a very high speed. A white, milky emulsion resulted.

Comparative Example IV

To 40.0 grams of octyltriethoxysilane was added 2.4 grams of alkanoxypolyethyleneoxy ethanol and 1.8 grams of cetyl trimethylammonium bromide. The mixture was stirred. To this mixture was added and mixed 55.8 grams of water.

Comparative Example V

To 40.0 grams of octyltriethoxysilane was added 5.0 grams of ARQUAD® 2HT75 and 1.0 grams of ETHOMEEN® C12. The mixture was stirred. To this mixture was added and mixed 54.0 grams of water.

Table I

Coating	Weight Gain (%) (after 10 Days)	Depth of Penetration	
		(Inches)	(cm)
No Coating	5.3%	-	
Example I	1.6%	0.20	0.508
Example II	1.5%	0.20	0.508
Example III	1.2%	0.20	0.508
Example IV	1.8%	0.20	0.508
Example V	1.7%	0.20	0.508
Example VI	1.8%	0.25	0.635
Comparative Example I	1.6%	0.20	0.508
Comparative Example II	2.0%	0.10	0.254
Comparative Example III	2.2%	0.10	0.254
Comparative Example IV	2.0%	0.10	0.254
Comparative Example V	1.5%	0.10	0.254

Claims

1. An aqueous emulsion consisting essentially of

a. 1.0 to 60 weight % of a silane;

b. 0.05 to 25 weight % of a quaternary ammonium compound of the general formula $R^1_a(R^2)_{4-a}N^+X^-$, where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length, X^- is an inorganic or organic anion, and a is 1 or 2.

2. The aqueous emulsion of claim 1, where the silane is of the general structure $R^1_aSi(OR^2)_{4-a}$ where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain configuration or aryl or aralkyl groups, R^2 are C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3).

3. The aqueous emulsion of claim 1, where X^- is a halide or acetate.

4. The aqueous emulsion of claim 1, additionally comprising nonionic surfactants present at about 0.1 to 1.0 weight percent of the emulsion.

5. The aqueous emulsion of claim 4, where the nonionic surfactant is a trialkyl amine.

6. The aqueous emulsion of claim 4, where the nonionic surfactant is an ethoxylated acetylinic hydrocarbon.

7. The aqueous emulsion of claim 1, where the weight ratio of silane to emulsifier is 4:1 to 20:1.

8. The aqueous emulsion of claim 1 additionally comprising a buffer.

9. The aqueous emulsion of claim 1 additionally comprising an organic solvent.

10. The aqueous emulsion of claim 1 where R_2 has a hydroxyl group.

Table I

Coating	Weight Gain (%) (after 10 Days)	Depth of Penetration	
		(Inches)	(cm)
No Coating	5.3%	-	
Example I	1.6%	0.20	0.508
Example II	1.5%	0.20	0.508
Example III	1.2%	0.20	0.508
Example IV	1.8%	0.20	0.508
Example V	1.7%	0.20	0.508
Example VI	1.8%	0.25	0.635
Comparative Example I	1.6%	0.20	0.508
Comparative Example II	2.0%	0.10	0.254
Comparative Example III	2.2%	0.10	0.254
Comparative Example IV	2.0%	0.10	0.254
Comparative Example V	1.5%	0.10	0.254

Claims

1. An aqueous emulsion consisting essentially of

a. 1.0 to 60 weight % of a silane;

b. 0.05 to 25 weight % of a quaternary ammonium compound of the general formula $R^1_a(R^2)_{4-a}N^+X^-$, where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length, X^- is an inorganic or organic anion, and a is 1 or 2.

2. The aqueous emulsion of claim 1, where the silane is of the general structure $R^1_aSi(OR^2)_{4-a}$ where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain configuration or aryl or aralkyl groups, R^2 are C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3).

3. The aqueous emulsion of claim 1, where X^- is a halide or acetate.

4. The aqueous emulsion of claim 1, additionally comprising nonionic surfactants present at about 0.1 to 1.0 weight percent of the emulsion.

5. The aqueous emulsion of claim 4, where the nonionic surfactant is a trialkyl amine.

6. The aqueous emulsion of claim 4, where the nonionic surfactant is an ethoxylated acetylinic hydrocarbon.

7. The aqueous emulsion of claim 1, where the weight ratio of silane to emulsifier is 4:1 to 20:1.

8. The aqueous emulsion of claim 1 additionally comprising a buffer.

9. The aqueous emulsion of claim 1 additionally comprising an organic solvent.

10. The aqueous emulsion of claim 1 where R_2 has a hydroxyl group.

11. A process for making a water-sealant composition comprising mixing:

a. 1.00 to 60 weight percent of a silane as defined in claims 1 or 2

b. 0.05 to 25 weight percent of a quaternary ammonium compound as defined in claims 1 or 3 and

c. 15 to 98.5 weight percent water,

to form an emulsion.

12. The use of an emulsifier as defined in claims 1 or 3 to emulsify a silane in order to obtain masonry water repellents comprising aqueous emulsions of the silanes.

Patentansprüche

1. Wäßrige Emulsion, bestehend im wesentlichen aus

a) 1,0 bis 60 Gew.-% eines Silans;

b) 0,05 bis 25 Gew.-% einer quaternären Ammoniumverbindung der allgemeinen Formel $R^1_a(R^2)_{4-a}N^+X^-$, worin R^1 Alkylgruppen mit 8 bis 22 Kohlenstoffen in der Länge sind, R^2 Alkylgruppen mit 1-3 Kohlenstoffen in der Länge sind, X^- ein anorganisches oder organisches Anion ist und a 1 oder 2 ist.

2. Wäßrige Emulsion gemäß Anspruch 1, wobei das Silan die allgemeine Struktur $R^1_aSi(OR^2)_{4-a}$ besitzt, worin R^1 C₁-C₁₈-Alkylgruppen in gerad- oder verzweigt-kettiger Konfiguration oder Aryl- oder Aralkylgruppen sind, R^2 C₁-C₅-Alkylgruppen in gerad- oder verzweigt-kettiger Konfiguration sind und a eins (1) bis drei (3) ist.

3. Wäßrige Emulsion gemäß Anspruch 1, wo X^- ein Halogenid oder Acetat ist.

4. Wäßrige Emulsion gemäß Anspruch 1, umfassend weiterhin nichtionische Tenside, die mit etwa 0,1 bis 1,0 Gew.-%, bezogen auf die Emulsion, vorliegen.

5. Wäßrige Emulsion gemäß Anspruch 4, wobei das nichtionische Tensid ein Trialkylamin ist.

6. Wäßrige Emulsion gemäß Anspruch 4, wobei das nichtionische Tensid ein ethoxylierter Acetylenkohlenwasserstoff ist.

7. Wäßrige Emulsion gemäß Anspruch 1, wobei das Gewichtsverhältnis von Silan zum Emulgiermittel 4 : 1 bis 20 : 1 beträgt.

8. Wäßrige Emulsion gemäß Anspruch 1, die weiterhin einen Puffer umfaßt.

9. Wäßrige Emulsion gemäß Anspruch 1, die weiterhin ein organisches Lösungsmittel umfaßt.

10. Wäßrige Emulsion gemäß Anspruch 1, wobei R_2 eine Hydroxylgruppe besitzt.

11. Verfahren zur Herstellung einer wasserabdichtenden Zusammensetzung, umfassend das Mischen von:

a) 1,00 bis 60 Gew.-% eines Silans, wie im Anspruch 1 oder 2 definiert;

b) 0,05 bis 25 Gew.-% einer quaternären Ammoniumverbindung, wie im Anspruch 1 oder 3 definiert, und

c) 15 bis 98,5 Gew.-% Wasser,

um eine Emulsion zu bilden.

12. Verwendung eines Emulgiermittels, wie im Anspruch 1 oder 3 definiert, zur Emulgierung eines Silans, um wasser-abstoßende Mittel für Mauerwerke zu erhalten, umfassend wäßrige Emulsionen der Silane.

Revendications

1. Emulsion aqueuse consistant essentiellement en

- 5 a. de 1,0 à 60% en poids d'un silane;
 b. de 0,05 à 25% en poids d'un composé d'ammonium quaternaire de la formule générale $R^1_a(R^2)_{4-a} N^+X^-$, où R^1 sont des groupes alkyles de huit à vingt-deux atomes de carbone en longueur, R^2 sont des groupes alkyles de 1-3 atomes de carbone en longueur, X^- est un anion inorganique ou organique, et a est égal à 1 ou à 2.
- 10 2. Emulsion aqueuse selon la revendication 1 dans laquelle le silane est de la structure générale $R^1_aSi(OR^2)_{4-a}$, où R^1 sont des groupes alkyles en C_1 - C_{18} dans une configuration de chaîne linéaire ou ramifiée ou des groupes aryles ou aralkyles, R^2 sont des groupes alkyles en C_1 - C_5 dans une configuration de chaîne linéaire ou ramifiée et a est compris entre un (1) et trois (3).
- 15 3. Emulsion aqueuse selon la revendication 1, dans laquelle X^- est un halogénure ou un acétate.
4. Emulsion aqueuse selon la revendication 1 comprenant en plus des tensioactifs nonioniques présents d'environ 0,1 à 1,0% en poids de l'émulsion.
- 20 5. Emulsion aqueuse selon la revendication 4, dans laquelle où le tensioactif nonionique est une trialkylamine.
6. Emulsion aqueuse selon la revendication 4, dans laquelle le tensioactif non-ionique est un hydrocarbure acétylénique éthoxylé.
- 25 7. Emulsion aqueuse selon la revendication 1, dans laquelle le rapport massique du silane à l'émulsifiant est de 4 :1 à 20:1.
8. Emulsion aqueuse selon la revendication 1 comprenant en plus un tampon.
- 30 9. Emulsion aqueuse selon la revendication 1 comprenant en plus un solvant organique.
10. Emulsion aqueuse selon la revendication 1, dans laquelle R^2 a un groupe hydroxyle.
- 35 11. Procédé de fabrication d'une composition de matériau d'étanchéité à l'eau comprenant le mélange :
 a) de 1,00 à 60% en poids d'un silane comme défini dans la revendication 1 ou 2.
 b) de 0,05 à 25% en poids d'un composé d'ammonium quaternaire comme défini dans la revendication 1 ou 3.
 c) de 15 à 98,5% en poids d'eau,
- 40 pour former une émulsion.
12. Utilisation d'un émulsifiant comme défini dans la revendication 1 ou 3 pour émulsifier un silane afin d'obtenir des matières hydrophobes de maçonnerie comprenant des émulsions aqueuses des silanes.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 631 999 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **94109082.1**

(51) Int. Cl.⁸: **C04B 41/49**

(22) Date of filing: **14.06.94**

(30) Priority: **30.06.93 US 84867**

(43) Date of publication of application:
04.01.95 Bulletin 95/01

(84) Designated Contracting States:
BE DE FR GB IT NL

(71) Applicant: **OSI SPECIALTIES, INC.**
39 Old Ridgebury Road
Danbury,
Connecticut 06817-0001 (US)

(72) Inventor: **Chen, Ming J.**
41 Poplar Road
Garnerville, N.Y. 10923 (US)
Inventor: **Chaves, Antonio**
27 Bryant Avenue
White Plains, N.Y. 10605 (US)

(74) Representative: **Wibbelmann, Jobst**
Wuesthoff & Wuesthoff,
Patent- und Rechtsanwälte,
Schweigerstrasse 2
D-81541 München (DE)

(54) **Cationic emulsions of alkylalkoxysilanes.**

(57) The present invention teaches masonry water repellents comprising aqueous emulsions of alkylalkoxysilanes with either a quaternary ammonium surfactant or a mixture of a quaternary ammonium surfactant with an amino and/or a nonionic surfactant. The alkylalkoxysilane is present at a level of about one to sixty weight percent of the final solution weight. The surfactants are present at levels of about 0.05 to 25 weight percent of the final solution weight. The useful quaternary ammonium surfactants are alkyltrimethyl or dialkyldimethyl ammonium compounds or quaternary ammonium modified dimethylpolysiloxanes. Amino and nonionic surfactants are used as additives to the quaternary surfactants. The types of nonionic surfactants contemplated herein are alkylamines and alkyl acetylenic alcohols.

EP 0 631 999 A2

Background

Concrete structures can undergo accelerated deterioration due to corrosion of the reinforcing steel rods. The corrosion is caused by the gradual introduction of chloride into the concrete from deicing salts.

5 Applying penetrating sealers can greatly diminish the intrusion of chloride into the concrete.

Solutions of alkyltrialkoxysilanes in organic solvents have been used very effectively to impart water repellent properties to porous masonry substrates such as mortar and concrete. These formulations penetrate the masonry substrate and provide a significant hydrophobic layer. However, solvent base formulations are undesirable due to the large amount of volatile organic components that are released into the air during their use. Various state regulations prohibit the volatile organic content (VOC) of an architectural coating from exceeding four hundred grams per liter.

The prior art solvent base coatings have not met these regulations. To reduce the amount of organic compounds released into the air, preparations of aqueous emulsions of alkyltrialkoxysilanes have been reported.

15 The utility of silanes in such aqueous emulsions, especially alkoxysilanes, as masonry water repellents is a widely known use because of their hydrophobic nature. For example, U.S. Patent No. 4,648,904 issued to DePasquale and Wilson teaches a porous masonry water repellent composition comprising: a hydrolyzable silane, an emulsifying agent and water. U.S. Patent No. 4,877,654 issued to Wilson teaches a similar composition but also contains a buffering compound to maintain the composition within the pH stable range. 20 U.S. Patent No. 5,074,912, issued to Liles and Klein also teaches a water repellent composition for treating porous substrates consisting of an emulsion containing water, at least one surfactant, and a siloxane. However, the emulsifiers taught therein are generally nonionic surfactants and only one type of silane (the active ingredient) may be used at a time in each emulsion. It has been found that nonionic emulsifiers, in particular highly ethoxylated surfactants, reduce the hydrophobic effect of these compositions. This leads to an increase in water absorption of the masonry material and in most cases a reduction in penetration depth of the silane. 25

Another example of prior art aqueous emulsions is taught in U.S. Patent No. 4,433,013 issued to Puhlinger, which discloses a water-sealant for inorganic porous mineral substrates which comprise an emulsion of at least one silane, one deactivatable surfactant, an organic alcohol, and water. The surfactants 30 taught as useful therein include fatty acid esters, and particularly alcohol/alkylene oxide adducts.

Moreover, in unrelated fields, the manufacture and use of quaternary ammonium pendant siloxane copolymers have been known. See U.S. Patent No. 4,895,964, issued to Margida. The uses in the prior art of such quaternary polysiloxanes have been in cosmetic preparations, as disclosed in the U.S. Patent No. 4,891,166, issued to Shaefer and Krakenberg and in waterproofing compositions with good fungicidal and mildewcidal properties, as disclosed in European Patent Application, Publication No. 0,469,624, to Yoshioka. 35

Summary of Invention

The present invention teaches masonry water repellents comprising aqueous emulsions of alkylalkoxysilanes with either a quaternary ammonium surfactant or a mixture of a quaternary ammonium surfactant 40 with an amino and/or a nonionic surfactant. The alkylalkoxysilane is present at a level of about one to sixty weight percent of the final solution weight. The surfactants are present at levels of about 0.05 to 25 weight percent of the final solution weight. The useful quaternary ammonium surfactants are alkyltrimethyl or dialkyldimethyl ammonium compounds or quaternary ammonium modified dimethylpolysiloxanes. Amino 45 and nonionic surfactants are used as additives to the quaternary surfactants. The types of nonionic surfactants contemplated herein are alkylamines and alkyl acetylenic alcohols.

Description of Invention

50 The present invention relates to the preparation of stable aqueous emulsions which impart hydrophobic properties to masonry materials and which penetrate into the masonry material to provide a significant hydrophobic layer. The term "masonry" is intended to include any porous inorganic substrate, particularly building compositions and including, but not limited to, structural ceramics such as common brick, paving brick, face conduits, roofing tile, flue lining, cements such as Portland cement, calcined gypsum products, 55 molding and building plaster and stucco, magnesia cement, insulation products such as electrical and thermal insulators (diatomaceous earth brick) and porcelain spark plugs. The term also includes stone, tile, artificial stone, adobe, concrete and reinforced concrete such as found in roadways, bridge decks, airport runways, parking garage decks, and other concrete building structures. The hydrophobic properties

imparted by the emulsion of the present invention applied over masonry surfaces protect the surfaces from corrosion, acidic rain, salt water and other degradents which water could otherwise deliver into the masonry.


An aqueous emulsion of the present invention consists of an alkylalkoxysilane or mixtures of alkylalkoxysilanes, emulsifiers and water. Optionally, a buffer may be added to maintain the pH of the emulsion in the preferred range of between 6 and 8. The alkylalkoxysilanes are the hydrophobic active ingredients in the emulsion that block the penetration of water into the masonry. The water is the solvent that carries the active ingredient into the masonry. The emulsifier is necessary to solubilize the silane in water. The buffer controls the pH of the solution.

The alkylalkoxysilanes for use herein are of the general structure $R^1_aSi(OR^2)_{4-a}$ where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain - configuration or aryl or aralkyl groups, R^2 may be C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3). The preferred R^1 is C_5 to C_{12} alkyl groups and R^2 is C_2 to C_4 alkyl groups. The most preferred silane for use herein is octyltriethoxysilane and octyltriisopropoxysilane. Alkyltrimethoxysilanes tend to hydrolyze more readily and decrease the shelf life of the emulsion and so are not preferred.

Moreover, mixtures of silanes may be used in emulsions of the present invention. By using a mixture of silanes in the emulsion one can choose one silane for its hydrophobic properties and another for its ability to penetrate masonry. Previously, mixtures of silanes could not be used because it was difficult to match two different silanes to a single emulsifier. Specific examples of silanes used in accordance with the present invention include, but are not limited to, methyltriethoxysilane, methyltri-n-propoxysilane, ethyltriethoxysilane, dimethyldimethoxysilane, dimethyldiethoxysilane, ethyltri-n-propoxysilane, propyltriethoxysilane, propyltri-n-propoxysilane, butyltriethoxysilane, dibutyldimethoxysilane, isobutyltrimethoxysilane, di-isobutyl-dimethoxysilane, isobutyltriethoxysilane, 4-chlorobenzyl triethoxysilane, 4-bromobenzyl tri-n-propoxysilane, phenyltriethoxysilane, octyltriethoxysilane, octyltriisopropoxysilane, dodecyltribromosilane, tetradecyltriethoxysilane, hexadecyltriethoxysilane, octadecyltriethoxysilane, mixtures thereof, and admixtures thereof with dimers, trimers and other oligomers thereof.

The emulsifiers for use herein include a quaternary ammonium surfactant or a mixture of quaternary ammonium surfactants with amino or specific nonionic surfactants. The quaternary ammonium surfactants are alkyl quaternary ammonium compounds or quaternary ammonium modified polysiloxanes. The quaternary ammonium compounds of the present invention are of the formula $R^1_aR^2_{4-a}N^+X^-$ where R^1 is C_8 to C_{22} alkyl group, R^2 are relatively short alkyl groups of 1-3 carbons in length and a is 1 or 2. Specific examples of quaternary ammonium surfactants useful in accordance with the present invention include, but are not limited to, the following examples: ARQUAD 2C-75, C-33W, C-50, 2HT-75, S-50, T-50, 12-37W, 12-50, 16-29W, 16-50 and 18-50 (commercially available from AKZO Chemicals, Inc. of Chicago, Illinois), JET QUAT C-50, S-2C-50, S-50, T-2C-50, T-50 and 2C-75 (commercially available from Jetco Chemicals, Inc. of Corsicana, Texas), M-QUAT 32-2475 (commercially available from Mazer Chemicals, Inc. of Mission Viejo, CA), TINEGAL MR-50 (commercially available from Ciba-Geigy Corp. of Basel, Switzerland), TOMAH Q-17-2, Q-18-15, Q-311, Q-511 and Q-D-T (commercially available from Tomah Products, Inc., a division of Exxon Chemical Co. of Milton, WI), and VARIQUAT A-200, B-200 and K-300 (commercially available from Sherex Chemical Co. Inc. of Dublin, Ohio).

The general formula of the quaternary ammonium modified polysiloxanes for use herein is $MeR^1R^3Si(OSiMeR^3)_x(OSiR^2R^3-M)_ySiR^1R^3Me$ where $x = 3-25$ and $y = 0-5$, with the preferred range for y being 2-3. The R^1 's may be chosen from Me or R^2-M and each R^1 may be different from one another. R^2 are bivalent hydrocarbon groups with at least three carbon atoms and not larger than 22, which may have a hydroxyl group and may be interrupted by an oxygen atom and each may be different from one another. R^3 may be a methyl, ethyl or phenyl group. M is




where R^3 , R^4 , R^5 are alkyl groups with 1 to 3 carbon atoms which may have hydroxy substitutions thereon. X^- is an inorganic or organic anion. Specific examples of the counter ion X^- include, but are not limited to, halides, acetate, citrate, bicarbonate, hydrogen phosphate, dihydrogen phosphate, sulfate, hydrogen sulfate

and methosulfate, while a halide or acetate is preferred. An example of the R²-M group is



- 5 A preferred silicone quaternary ammonium chloride is where y = 0 and has the formula of:



15 where R² and M are as above. Also note that while the dimethyl siloxane is the preferred building block for the polysiloxane copolymer, diethyl or phenylmethyl siloxane may also be used herein as the building block for the copolymer.

Y varies proportionally to the need for aqueous compatibility of the surfactant. Similarly, the larger the alkyl group of the silane (the active ingredient), the larger the hydrophobic group (x of the emulsifier) needs to be.

Co-surfactants may be used as additives with the quaternary ammonium surfactants. The types of surfactants useful for such a purpose are alkyl amines, which become protonated in the aqueous solution, and nonionics which are hydroxylated ethoxylated acetylenic hydrocarbons, such as ethoxylated tetramethyl decynediol (SURFYNOL 420, available from Air Products of Allentown, Pennsylvania). In distinction, ethoxylated amines (e.g., bis(2-hydroxyethyl) cocoamine (ETHOMEEN C/12 available from Akzo Chemicals Inc. of Chicago, Illinois)) have been found not to be effective for this purpose. The ethoxylated acetylenic hydrocarbon nonionics, for this purpose, should only be present at about 0.1 to 1.0 weight percent of the total emulsion and preferably about 0.3 weight percent. The alkyl amines have been found effective at weight percentages about equal to those of the quaternary ammonium surfactant present.

Specific examples alkyl amines useful as co-surfactants in accordance with the present invention include, but are not limited to, dodecylamine, hexadecylamine, octadecylamine, amines derived from coconut oil, hardened tallow, tallow, soya, methyl dicoco amine, methyl dihydrogenated tallow amine, dimethyl cocoamine, dimethyl dodecyl amine, and dimethyl hexadecyl amine. Specific examples of nonionic surfactants useful as co-surfactants in accordance with the present invention include, but are not limited to, SURFYNOL 61, 82, 104, 420, 440 and 465 (available from Air Products).

Optionally, a small amount of organic solvent can be used as an additional stabilizer. These organic solvents have a synergistic affect on the emulsion and are not intended to be added at the level of a solvent, but act rather as a stabilizer of the emulsion. Said solvents should be added at less than 10.0 weight percent of the emulsion, and preferably at about 1-2 weight percent. Specific examples of solvents useful in accordance with the present invention include, but are not limited to, alcohols such as methanol, ethanol, propanol, 2-propanol, butanol, 2-methyl-2-propanol, 2-butanol and pentanol.

The silane may be present in an amount ranging from 1.0 to 60 weight percent of the emulsion. Varying the amount of silane in the emulsion changes the performance of the emulsion since the silane is the active ingredient. The emulsifier is present in an amount ranging from 0.05 to 25 weight percent of the emulsion. The greater the amount of silane, the greater the amount of emulsifier required to solubilize the silane in water. The weight ratio of silane to emulsifier should be about 1:1 to 120:1 and preferably is about 10:1. Water is present in an amount ranging from 15 to 98.95 weight percent of the emulsion.

The aqueous emulsions are typically prepared by mixing the surfactant or mixture of surfactants with an alkyltrialkoxysilane or a mixture of alkylalkoxysilanes. Water is then added and the mixture is blended to provide a white, milky emulsion. The pH of the resulting emulsion may be adjusted to provide a final emulsion with a pH of 7.0 ± 1.0. A pH outside of this range is possible, but it shortens the shelf life of the emulsion. Substances which can be used to adjust the pH are organic or inorganic buffers including sodium acetate, sodium citrate, sodium carbonate, sodium bicarbonate, sodium hydrogen phosphate, sodium dihydrogen phosphate, the corresponding potassium salts, and organic amines and their salts. When organic amine surfactants are used as co-emulsifiers, the addition of buffer usually is not required because the pH is normally in the desired range of 6 to 8.

The emulsions of the present invention may be applied onto the surface to be protected in a variety of ways that are well known in the art, including, but not limited to, brushing, spraying and rolling the emulsion on the surface.

When an emulsion of the present invention was applied at the rate of 125 square feet per gallon as a single coat, the industry standard for testing, it reduced the water gain of a two-inch concrete cube by approximately 70 percent and the silane had a penetration depth of at least 0.2 inches. A typical emulsion prepared with surfactants has a penetration depth of only 0.1 inches.

Examples

Coating and Testing Procedure

The penetrating sealers described below were applied to two-inch concrete cubes at a rate of 125 square feet per gallon with a small, bristle brush and allowed to cure on a wire rack for two days at ambient conditions. The coated cubes were weighed and then completely immersed in a water bath so that the concrete was more than one inch below the water surface. The cubes were weighed daily and the percentage weight increase was determined. When the soaking test was completed, the cubes were allowed to dry at ambient conditions in a laboratory hood. After the cubes were allowed to dry, they were broken in half. The inner surface of each cube was sprayed with water and the depth of penetration of the sealer was determined as a visible dry area of the concrete below the coated surface. This was easily measured with a ruler or caliper. The results of the sealers described below are set forth in Table I.

Example I

To 13.4 grams of octyltriethoxysilane was added 3.0 grams of dimethyldicocoammonium chloride (ARQUAD 2C-75 available from Akzo Chemicals Inc. of Chicago, Illinois). The mixture was stirred with a stirring bar for 30 minutes. To this mixture was then added 33.6 grams of deionized water and the mixture was stirred vigorously. A milky white emulsion resulted. The pH of the emulsion was adjusted with sodium phosphate dibasic to give a final pH of 7.4.

Example II

To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD 2C-75 in an Oster blender and mixed at low speed for one minute. 58.0 grams of water buffered to a pH of 7.0 with a phosphate buffer was added to the mixture and the mixture was stirred at a high speed for five minutes resulting in a white, milky emulsion. The pH of the resulting emulsion was found to be 6.8.

Example III

To 3.5 grams of octyltriethoxysilane and 0.5 grams of 1,10-bis(trimethoxysilyl)decanewas added 0.4 grams of ARQUAD 2C-75. The mixture was stirred with a magnetic stirring bar. To this mixture was then added 5.6 grams of deionized water and the mixture was stirred vigorously. A white milky emulsion resulted. To the emulsion was added 0.02 grams of SURFYNOL 420. The emulsion was stirred for an additional thirty minutes.

Example IV

To 3.5 grams of octyltriethoxysilane and 0.5 grams of 1,10-bis(trimethoxysilyl) decane was added 0.3 grams of ARQUAD 2C-75 and 0.05 grams of dimethyl di(hydrogenated-tallow)ammonium chloride (ARQUAD 2HT75 available from Akzo Chemicals Inc. of Chicago, Illinois). The mixture was stirred with a magnetic stirring bar. To this mixture was added 5.65 grams of deionized water and the mixture was stirred vigorously for four hours. A white milky emulsion resulted.

Example V

To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD 2C-75, and 2.0 grams of cocodimethyl amine (ARMEEN DMCD available from Akzo Chemie America). The mixture was blended at low speed. To this mixture was added and blended at high speed 56.0 grams of water. A white emulsion

resulted.

Example VI

5 To 40.0 grams of octyltriethoxysilane was added 2.0 grams of ARQUAD 2C-75 and 2.0 grams of ARMEEN DMCD. The mixture was stirred. To this mixture was added and mixed at high speed 55.7 grams of water. Finally, 0.3 grams of SURFONYL 420 was added and the mixture was stirred for thirty minutes.

Example VII

10 To 2 grams of octyltriethoxysilane was added 0.25 grams of $M^*D_9M^*$ where M^* is $Me_2Si(O)-C_3H_6OCH_2CH(OH)CH_2NMe_3^+ Cl^-$ and D is $(OSiMe_2)$. The mixture was stirred with a stirring bar for 30 minutes. Afterwards, 2.74 grams of deionized water was added to the mixture and the mixture was stirred vigorously. A milky white emulsion resulted. To the emulsion was added 0.015 grams of SURFYNOL 420.
15 The emulsion was stirred an additional 30 minutes. A stable milky white emulsion resulted.

Example VIII

20 To 48.66 grams of octyltriethoxysilane was added 4.87 grams of $M^*D_9M^*$, where M^* is $Me_2Si(O)-C_3H_6OCH_2CH(OH)CH_2NMe_3^+ Cl^-$ and D is as above, in an Oster blender and mixed at low speed for one minute. 67.76 grams of deionized water was added and the mixture was stirred at a high speed for five minutes resulting in a white, milky emulsion. To the emulsion was added 0.365 grains of SURFYNOL 420 and the mixture was stirred overnight with a magnetic stirrer.

25 Example IX

To 2.5 grams of octyltriethoxysilane was added 0.3 grams of $MD_{18}D^*M$, where D^* is $MeSi(O)-C_3H_6OCH_2CH(OH)CH_2NMe_3^+ Cl^-$ and M is $OSi(Me)_3$, and 0.5 grams of isopropyl alcohol. The mixture was stirred with a magnetic stirring bar. To this mixture was added 2.8 grams of water and the mixture was
30 stirred vigorously for several hours. A white, milky emulsion resulted.

Comparative Example I

To 30 grams of absolute ethyl alcohol was added 20 grams of octyltriethoxysilane to make a 40% by
35 weight silane solution.

Comparative Example II

40 To 20.0 grams of octyltriethoxysilane was added 0.56 grams of octylphenoxypolyethoxy ethanol and 0.24 grams of octylphenoxypolyethoxy ethanol [differentiate] in an Oster blender. The mixture was stirred at a low speed for one minute. Deionized water, 29.2 grams, was added quickly and the mixture was blended at a high speed for five minutes. A white, milky emulsion resulted.

Comparative Example III

45 To 30.0 grams of octyltriethoxysilane was added 0.42 grams of alkyloxypolyethyleneoxy ethanol (primary alcohol) and 0.78 grams of alkyloxypolyethyleneoxy ethanol (secondary alcohol) in an Oster blender at a low speed for one minute. 43.8 grams of deionized water was added and the mixture was blended for five minutes at a very high speed. A white, milky emulsion resulted.

50 Comparative Example IV

To 40.0 grams of octyltriethoxysilane was added 2.4 grams of alkanoxypolyethyleneoxy ethanol and 1.8 grams of cetyl trimethylammonium bromide. The mixture was stirred. To this mixture was added and mixed
55 55.8 grams of water.

Comparative Example V

To 40.0 grams of octyltriethoxysilane was added 5.0 grams of ARQUAD 2HT75 and 1.0 grams of ETHOMEEN C12. The mixture was stirred. To this mixture was added and mixed 54.0 grams of water.

Table I

Coating	Weight Gain (%) (after 10 Days)	Depth of Penetration (Inches)
No Coating	5.3%	-
Example I	1.6%	0.20
Example II	1.5%	0.20
Example III	1.2%	0.20
Example IV	1.8%	0.20
Example V	1.7%	0.20
Example VI	1.8%	0.25
Example VII	1.6%	0.20
Example VIII	1.7%	0.25
Example IX	1.7%	0.25
Comparative Example I	1.6%	0.20
Comparative Example II	2.0%	0.10
Comparative Example III	2.2%	0.10
Comparative Example IV	2.0%	0.10
Comparative Example V	1.5%	0.10


Claims

1. An aqueous emulsion comprising
 - a. 1.0 to 60 weight percent of a silane;
 - b. 0.05 to 25 weight percent of an emulsifier selected from the group consisting of (1) quaternary ammonium halides of the general formula $R^1_a(R^2)_{4-a}N^+X^-$ where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length and X^- is an inorganic or organic anion and (2) quaternary ammonium modified polysiloxanes of the general formula



where $x = 3-25$, $y = 0-5$,

R_1 is selected from the group consisting of Me or R_2-M , where R_2 is a bivalent hydrocarbon group having at least four carbon atoms and M is




- where R^3 , R^4 , R^5 are alkyl groups with 1 to 3 carbon atoms and X^- is an inorganic or organic anion; and
- c. 15 to 98.5 weight percent water.

2. The aqueous emulsion of claim 1, where the silane is of the general structure $R^1_aSi(OR^2)_{4-a}$ where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain configuration or aryl or aralkyl groups, R^2 are C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3).


3. The aqueous emulsion of Claim 1, where X^- is a halide or acetate.

4. The aqueous emulsion of Claim 1, where the emulsifier is a quaternary modified polysiloxane and $y = 0$.
5. The aqueous emulsion of claim 1, additionally comprising nonionic surfactants present at about 0.1 to 1.0 weight percent of the emulsion.
6. The aqueous emulsion of claim 5, where the nonionic is a trialkyl amine.
7. The aqueous emulsion of claim 5, where the nonionic is an ethoxylated acetylinic hydrocarbon.
8. The aqueous emulsion of claim 1, where the weight ratio of silane to emulsifier is about 4:1 to 20:1.
9. The aqueous emulsion of claim 1 additionally comprising a buffer.
10. The aqueous emulsion of claim 1 additionally comprising an organic solvent.
11. The aqueous emulsion of claim 1 where R_2 has hydroxyl group.
12. The aqueous emulsion of claim 1, where the emulsifier is a quaternary ammonium modified polysiloxane and R_2 -M group is $-C_3H_6OCH_2CH(OH)CH_2NMe_3^+Cl^-$.
13. An aqueous emulsion comprising
 - a. 1.0 to 60 weight percent of at least two silanes;
 - b. 0.05 to 25 weight percent of an emulsifier; and
 - c. 15 to 98.5 weight percent water.
14. An emulsion according to claim 13 wherein the emulsifier is selected from the group consisting of (1) quaternary ammonium halides of the general formula $R^1a(R^2)_{4-a}N^+X^-$, where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length, and X^- is an inorganic or organic anion and (2) quaternary ammonium modified polysiloxanes of the general formula $Me_2R_1Si(OSiMe_2)_x(OSiMeR_2-M)_ySiR_1Me_2$ where $x = 3-25$, $y = 0-5$, R_1 is selected from the group consisting of Me or R_2 -M, R_2 is a bivalent hydrocarbon group having at least four carbon atoms, and M is




where R^3 , R^4 , R^5 are alkyl groups with 1 to 3 carbon atoms and X^- is an inorganic or organic anion.

15. A process for making a water-sealant composition comprising mixing:
 - a. 1.00 to 60 weight percent of a silane;
 - b. 0.05 to 25 weight percent of an emulsifier selected from the group consisting of (1) quaternary ammonium halides of the general formula $R^1a(R^2)_{4-a}N^+X^-$ where R^1 are alkyl groups of eight to twenty-two carbons in length, R^2 are alkyl groups of 1-3 carbons in length, and X^- is an inorganic or organic anion and (2) quaternary ammonium modified polysiloxanes of the general formula



where $x = 3-25$, $y = 0-5$,

R_1 is selected from the group consisting of Me or R_2 -M, R_2 is a bivalent hydrocarbon group having at least four carbon atoms, and M is



5

10

where R^3 , R^4 , R^5 are alkyl groups with 1 to 3 carbon atoms and X^- is an inorganic or organic anion;
and
c. 15 to 98.95 weight percent water,
to form an emulsion.

15

16. The aqueous emulsion of claim 15, where the silane is of the general structure $R^1_a Si(OR^2)_{4-a}$ and where R^1 is C_1 to C_{18} alkyl groups in straight or branched chain configuration or aryl or aralkyl groups, R^2 are C_1 to C_5 alkyl groups in straight or branched chain configuration and a is one (1) to three (3).

17. The aqueous emulsion of claim 15, where X^- is a halide or acetate.

20

18. The aqueous emulsion of claim 15, additionally comprising nonionic surfactants present at about 0.1 to 1.0 weight percent of the emulsion.

19. The aqueous emulsion of claim 15, where the weight ratio of silane to emulsifier is about 4:1 to 20:1.

25

20. The aqueous emulsion of claim 15 where R_2 has hydroxyl group.

30


35

40

45

50

55



5

10

where R³, R⁴, R⁵ are alkyl groups with 1 to 3 carbon atoms and X⁻ is an inorganic or organic anion;
and
c. 15 to 98.95 weight percent water,
to form an emulsion.

15

16. The aqueous emulsion of claim 15, where the silane is of the general structure R¹_aSi(OR²)_{4-a} and
where R¹ is C₁ to C₁₈ alkyl groups in straight or branched chain configuration or aryl or aralkyl groups,
R² are C₁ to C₅ alkyl groups in straight or branched chain configuration and a is one (1) to three (3).

17. The aqueous emulsion of claim 15, where X⁻ is a halide or acetate.

20

18. The aqueous emulsion of claim 15, additionally comprising nonionic surfactants present at about 0.1 to
1.0 weight percent of the emulsion.

19. The aqueous emulsion of claim 15, where the weight ratio of silane to emulsifier is about 4:1 to 20:1.

25

20. The aqueous emulsion of claim 15 where R₂ has hydroxyl group.

30

35

40

45

50

55



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 631 999 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **94109082.1**

(51) Int. Cl.⁶: **C04B 41/49**

(22) Date of filing: **14.06.94**

(30) Priority: **30.06.93 US 84867** ...

(43) Date of publication of application:
04.01.95 Bulletin 95/01

(84) Designated Contracting States:
BE DE FR GB IT NL

(88) Date of deferred publication of the search report:
25.01.95 Bulletin 95/04

(71) Applicant: **OSI SPECIALTIES, INC.**
39 Old Ridgebury Road
Danbury,
Connecticut 06817-0001 (US)

(72) Inventor: **Chen, Ming J.**
41 Poplar Road
Garnerville, N.Y. 10923 (US)
Inventor: **Chaves, Antonio**
27 Bryant Avenue
White Plains, N.Y. 10605 (US)

(74) Representative: **Wibbelmann, Jobst**
Wuesthoff & Wuesthoff,
Patent- und Rechtsanwälte,
Schweigerstrasse 2
D-81541 München (DE)

(54) **Cationic emulsions of alkylalkoxysilanes.**

(57) The present invention teaches masonry water repellents comprising aqueous emulsions of alkylalkoxysilanes with either a quaternary ammonium surfactant or a mixture of a quaternary ammonium surfactant with an amino and/or a nonionic surfactant. The alkylalkoxysilane is present at a level of about one to sixty weight percent of the final solution weight. The surfactants are present at levels of about 0.05 to 25 weight percent of the final solution weight. The useful quaternary ammonium surfactants are alkyltrimethyl or dialkyldimethyl ammonium compounds or quaternary ammonium modified dimethylpolysiloxanes. Amino and nonionic surfactants are used as additives to the quaternary surfactants. The types of nonionic surfactants contemplated herein are alkylamines and alkyl acetylenic alcohols.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 94 10 9082

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X,P	DATABASE WPI Derwent Publications Ltd., London, GB; AN 94-148131 & JP-A-6 093 254 (TOYO INK) 5 April 1994 * abstract *	1-3,5	C04B41/49
A	--- DATABASE WPI Derwent Publications Ltd., London, GB; AN 82-60673E & JP-A-57 095 882 (TORAY SILICONE) 14 June 1982 * abstract *	1	
A	--- US-A-5 209 775 (BANK ET AL) * claim 1 *	1	
A,D	--- US-A-4 648 904 (DEPASQUALE ET AL) * column 3, line 19 - line 20; claim 1 *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C04B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 17 November 1994	Examiner Lentz, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			